

LIMITED WARRANTY

DenMat will replace or refund the purchase price of any of its products that are proven to be defective within 30 days of the purchase date. Replacement of defective goods, or refund of the purchase price, shall be the exclusive remedy for the user. DenMat will not be liable for any economic, incidental, or consequential loss or damage that arises out of the use of, or the inability to use its products.

This limited warranty is in lieu of all other warranties, expressed or implied, and shall be void if the product is improperly stored or used. There are no implied warranties of merchantability, fitness for a particular purpose, or otherwise. Before using this product, the user shall determine whether it is suitable for the intended use and the user shall assume all risk and liability associated therewith.

DENMAT CUSTOMER SUPPORT

U.S. and Canada Customer Service.....800-433-6628
U.S. and Canada Fax Orders and Inquiries.....800-233-6628
International Inquiries.....805-347-7990
International Fax Orders and Inquiries:805-347-7983
Websitedenmat.com

SAFETY DATA SHEETS AVAILABLE AT denmat.com

©2019 Den-Mat Holdings, LLC. All rights reserved. 750454172 R:3 05/19/2019



Geristore®

Dual-Cure Resin-Ionomer Introductory Kit



Symbols Glossary available at:
denmat.com/symbols



Den-Mat Holdings, LLC
1017 W. Central Avenue
Lompoc, CA 93436 USA



MDSS GmbH
Schiffgraben 41
30175 Hannover, Germany



Geristore is a fluoride-releasing, radiopaque, hydrophilic, restorative material. Geristore’s physical properties include low cure shrinkage, low coefficient of thermal expansion, and high strength. The material aggressively bonds to dentin, enamel, composite, porcelain, and metal, including stainless steel. The dual-cure formulation assures the integrity of the restoration in areas difficult to light-cure.

CAUTION: Wear protective gloves while using this product.

CAUTION: Wear eye protection while using this product.

CAUTION: Geristore has not been studied in children, pregnant or breast-feeding women.

DIRECT RESTORATIONS

Note: Remove Geristore from the refrigerator about 30 minutes before use.

1. Clean tooth surface(s) thoroughly.
2. Prepare the tooth surface according to the type of surface you will be bonding to:
 - a. DENTIN and ENAMEL: For maximum bond strengths, the Tenure® Multi-Purpose Bonding System should be applied prior to the use of Geristore.
 - b. COMPOSITE/METAL:
 - Roughen surface with diamond or sandblaster.
 - Thoroughly wash and air-dry.
 - Apply Dry Bond to degrease and assure that there is a clean, dry surface.
3. Select the appropriate Geristore B shade paste. Optimum shading is achieved with a 50/50 mix of Geristore A and B paste shades.

RELATED DENMAT PRODUCTS

Description

Part Number

Tenure® Uni-Bond® with Gloss-N-Seal®	030411900
Tenure Multi-Purpose Bonding System	031146000
Virtuoso® Flowable Custom 15 Shade Kit	030381800
Tenure S Value Kit	031145100
Virtuoso Universal Intro Kit	030381950
Sapphire® Plus Plasma Arc Curing Light	033968000
FLASHlite® Magna 4.0 LED Curing Light	CR1079
Centrix Tip/Plug 25pc	030057001
Centrix Mark II Syringe 1pc	38115

- e. Maintain a log including material, shade and associated curing exposure time. Use the log to monitor system performance.

Note: If a cavity preparation is deep, curing exposure times must also be increased due to beam divergence and angular placement of the light transmitting element to the restoration. An incremental filling technique is recommended and each increment should be fully cured prior to applying additional layers.

General guidelines for curing light unit exposure times.

See manufacturer's instructions. ALWAYS bench test restorative materials before use in vivo.

- Curing lights with power density greater than 800 mW/cm². Cure the buccal and lingual with 10-second exposures for each area.
- Curing lights with power density less than 800 mW/cm². Cure the buccal and lingual for 20-second exposures for each area.
- Curing lights with power density less than 300 mW/cm² should not be used to cure.

STORAGE

Do not freeze.

Do not expose to direct sunlight.

Do not expose to temperatures exceeding 77° F (25° C).

Refrigerate for maximum shelf life.

Return to room temperature prior to use.

4. Prior to withdrawing Geristore Paste A, briefly stir paste in jar. Place equal amounts of Geristore A and B pastes onto mixing pad. Mix well with a plastic mixing stick (do not use metal) until a smooth homogeneous paste is obtained.

5. Dispense Geristore onto the area to be restored.

Note: Centrix tips and plugs (No.030057001) and delivery syringe (No.38115) can be used to deliver the mixed material more precisely.

Note: The Geristore regular set material will reach final cure in 4 minutes and the slow set material will reach final cure in 7 minutes from the time mixed. The working time is 1 ½ minutes for Geristore regular set material and 2 minutes for the slow set material, unless the material is light-cured. To determine the correct curing times for your curing light(s), we recommend that you use standard 2mm deep curing test rings.

6. Finishing: For esthetic areas, apply a thin layer of Virtuoso® Flowable Clear (No.030381827). Finish with a 12 or 30 fluted bur and polish.

BASE AND LINER

1. Apply the Geristore® mixture to dentin surfaces and light-cure.
2. Complete the restoration with Virtuoso Universal Composite or take an impression for an indirect restorative. Geristore is compatible with any Bis-GMA-based restorative.

CEMENTING INDIRECT RESTORATIONS

(Metal and PFM Crowns, Inlays, Onlays, Bridges)

Geristore can also be used to cement metal and PFM crowns, bridges, inlays, and onlays. Seat the restoration and remove the excess material at the gel stage.

Note: For Maryland Bridges and other restorations with little or no mechanical retention, we recommend applying the Tenure® Multi-Purpose Bonding System to dentin or enamel prior to the application of Geristore.

1. Using a plastic instrument, coat tooth surface(s) and prepared bonding surface of indirect restorative with the Geristore mixture. Seat the restorative, noting excess Geristore escaping from all margins.
2. Take care not to disturb the restoration. Remove the excess after gel time (approximately 1½ - 2 minutes) but before final cure.
3. After the final set, finish the margins with a fine diamond or a 12 or 30 fluted bur.

ORTHODONTIC APPLIANCES

1. For brackets, etch the teeth and apply Tenure Multi-Purpose Bonding System (No. 031146000) to the enamel. Coat the Geristore mixture onto the bracket and seat the bracket. Remove excess material with a sable brush dipped in Tenure S (No. 031145100).

2. For bands, apply Tenure to the inside surface of the band and to the enamel. Coat the inside surface of the band and tooth with the Geristore mixture and slide the band into place. Remove excess with a sable brush dipped in Tenure S. Geristore is compatible with any esthetic orthodontic hardware (porcelain, acrylic, or plastic).
3. Light-cure the brackets or bands.

Due to variations in the performance characteristics of light curing units, ALWAYS bench test restorative materials before use in vivo.

- a. Using standard 2 mm curing test rings, fill the well of the test ring and level material.
- b. Position the light transmitting element perpendicular to and approximately 2 mm-5 mm above the top surface of the ring.
 - With Sapphire® PAC lights (all models) start with 5-second exposures.
 - With Flashlite® LED lights (all models) start with 10-second exposures.
 - For all other curing lights; halogen, LED and others, refer to the manufacturer's instructions. A minimum of 10-30 seconds is recommended.
- c. Use a dental probe to scrape test the hardness of the top and bottom surfaces. The bottom surface should be as hard as the top surface.
- d. If the bottom surface is not completely cured, repeat steps (b) to (c). Repeat until the bottom surface is completely cured.